



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08K 5/5333, C08L 67/02, C08J 11/04	A1	(11) International Publication Number: WO 96/11978 (43) International Publication Date: 25 April 1996 (25.04.96)
(21) International Application Number: PCT/EP95/03937 (22) International Filing Date: 5 October 1995 (05.10.95) (30) Priority Data: 3090/94-0 14 October 1994 (14.10.94) CH (71) Applicant (for all designated States except US): CIBA-GEIGY AG [CH/CH]; Klybeckstrasse 141, CH-4002 Basle (CH). (72) Inventors; and (75) Inventors/Applicants (for US only): PFAENDNER, Rudolf [DE/DE]; Sackgasse 3, D-64668 Rimbach (DE). HOFFMANN, Kurt [DE/DE]; Am Kohengraben 30, D-64686 Lautertal (DE). HERBST, Heinz [DE/DE]; Hohensteiner Strasse 40, D-64686 Lautertal (DE). (74) Common Representative: CIBA-GEIGY AG; Patentabteilung, Klybeckstrasse 141, CH-4002 Basle (CH).		(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, IS, JP, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK, TJ, TM, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: INCREASING THE MOLECULAR WEIGHT OF POLYCONDENSATES (57) Abstract The invention relates to a process for increasing the molecular weight of polycondensates, which comprises heating a polycondensate in the temperature range below the melting point and above the glass transition temperature in the solid phase of the polymer with addition of at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Increasing the molecular weight of polycondensates

The invention relates to a process for increasing the molecular weight of polycondensates and to the polycondensates obtainable by the process.

Polycondensates, such as polyamides, polyesters and polycarbonates, are important engineering plastics with a wide variety of potential uses, for example in the form of films, bottles, fibres and injection mouldings. It is common to these polymers that they are prepared by polycondensation reactions. For technical or kinetic reasons, the synthesis of these polymers frequently does not give high molecular weights. Polymers having high molecular weights are therefore prepared by condensation in the solid phase.

Damage to such polycondensates during processing and use predominantly results, owing to chain cleavage, in polymer fragments containing functional terminal groups. Since the mechanical and physical properties are crucially dependent on the molecular weight of the polymer, high-quality recycling of used polyamides, polyesters and polycarbonates and their production waste, for example from fibre production and injection moulding, is frequently only possible to a restricted extent without aftertreatment owing to the reduced molecular weight.

An improvement in the material properties of used or thermally or hydrolytically pre-damaged polycondensates is possible in principle. For example, they can be subjected to post-condensation in the solid state [S. Fakirov, *Kunststoffe* 74, 218 (1984) and R.E. Grützner et al., *Kunststoffe* 82, 284 (1992)]. However, this known method is protracted, and in addition is sensitive to impurities, as may be present in used material.

Furthermore, EP-0 410 230 has proposed carrying out the solid-phase condensation of polyamides using phosphoric acid, phosphorous acid or phosphonous acid as catalyst.

F. Mitterhofer has described studies using a diphosphonite as processing stabilizer in polymer recyclates (C.A. 91, 124534).

EP-A-0 090 915 describes a process for the condensation of poly(alkylene terephthalate) in the solid phase in the presence of esters of phosphorous acid, for example triphenyl phosphite, at from 25 to 65°C below the melting point of the poly(alkylene terephthalate) while passing a stream of inert gas through the mixture.

- 2 -

The present invention therefore had the object of developing a process for post-condensation in the solid phase which allows an increase in the molecular weight of polycondensates, such as polyesters, polyamides and polycarbonates, and of corresponding copolymers and blends in a relatively short time and/or improves the properties of the polycondensate.

The invention thus relates to a process for increasing the molecular weight of polycondensates, which comprises heating a polycondensate in the temperature range below the melting point and above the glass transition temperature in the solid phase of the polymer with addition of at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester.

This increase in molecular weight results in an improvement in the properties of the polycondensates, which becomes evident, for example, in the injection-moulding sector, extrusion sector and in particular in recyclates. With the aid of the novel process, an increase in molecular weight can be achieved, in particular, in polycondensate recyclates from the collection of used industrial parts, for example from automobile and electrical applications. This allows recyclates to be re-used for high-quality applications, for example as high-performance fibres, injection mouldings, extrusion applications or foams. Such recyclates also originate, for example, from industrial or domestic collections of valuable materials, from production waste, for example from fibre production and trimmings, or return obligations, for example collections of PET drinks bottles.

The invention also relates to a process for increasing the molecular weight of polycondensates, which comprises heating a polycondensate in the temperature range below the melting point and above the glass transition temperature in the solid phase of the polymer with addition of at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester and in the presence of at least one polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyl-lactams, maleimides, alcohols, carbodiimides and esters.

The invention furthermore relates to the preparation of branched, crosslinked and partially crosslinked polycondensates. This can be carried out, in particular, by addition of the abovementioned polyfunctional compounds. An insoluble polycondensate is obtained which can be used, for example, for the production of foams.

The polycondensate is preferably a recycled polycondensate.

The novel process is of particular interest when the polycondensate is a polyamide, a polyester, a polycarbonate or a copolymer thereof.

Besides polyesters, polyamides and polycarbonates, the present invention also covers the corresponding copolymers and blends, for example PBT/PS, PBT/ASA, PBT/ABS, PBT/PC, PET/ABS, PET/PC, PBT/PET/PC, PBT/PET, PA/PP, PA/PE and PA/ABS. However, it must be taken into account that the novel process, like all methods allowing exchange reactions between the blend components, can result in a modification of the blend, i.e. in the formation of copolymeric structures.

The term polyamides, i.e. both fresh polyamides and recycled polyamides, is taken to mean aliphatic and aromatic polyamides or copolyamides derived from diamines and dicarboxylic acids and/or from amino carboxylic acids or the corresponding lactams. Examples of suitable polyamides are: PA 6, PA 11, PA 12, PA 46, PA 66, PA 69, PA 610, PA 612, PA 10.12, PA 12.12, and amorphous polyamides of the Trogamid PA 6-3-T and Grilamide TR 55 type. Polyamides of this type are known in general terms and are commercially available.

The polyamides are preferably crystalline or partially crystalline polyamides and in particular are PA 6 and PA 6.6 or mixtures thereof, and recyclates or copolymers based thereon.

Polyesters, i.e. both fresh polyesters and recycled polyesters, can be homopolyesters or copolyesters built up from aliphatic, cycloaliphatic or aromatic dicarboxylic acids and diols or hydroxycarboxylic acids.

The aliphatic dicarboxylic acids can contain from 2 to 40 carbon atoms, the cycloaliphatic dicarboxylic acids can contain from 6 to 10 carbon atoms, the aromatic dicarboxylic acids can contain from 8 to 14 carbon atoms, the aliphatic hydroxycarboxylic acids can contain from 2 to 12 carbon atoms and the aromatic and cycloaliphatic hydroxycarboxylic acids can contain from 7 to 14 carbon atoms.

The aliphatic diols can contain from 2 to 12 carbon atoms, the cycloaliphatic diols can

contain from 5 to 8 carbon atoms and the aromatic diols can contain from 6 to 16 carbon atoms.

The term aromatic diols is taken to mean diols in which two hydroxyl groups are bonded to one or to different aromatic hydrocarbon radicals.

It is furthermore possible for the polyesters to be branched by small amounts, for example 0.1 to 3 mol %, based on the dicarboxylic acids present, of monomers having a functionality of greater than two (for example pentaerythritol, trimellitic acid, 1,3,5-tri-(hydroxyphenyl)benzene, 2,4-dihydroxybenzoic acid or 2-(4-hydroxyphenyl)-2-(2,4-dihydroxyphenyl)propane).

In polyesters comprising at least two monomers, the latter can be randomly distributed or arranged in the form of blocks.

Suitable dicarboxylic acids are linear and branched, saturated, aliphatic dicarboxylic acids, aromatic dicarboxylic acids and cycloaliphatic dicarboxylic acids.

Suitable aliphatic dicarboxylic acids are those having from 2 to 40 carbon atoms, for example oxalic acid, malonic acid, dimethylmalonic acid, succinic acid, pimelic acid, adipic acid, trimethyladipic acid, sebacic acid, azelaic and dimeric acids (products of the dimerization of unsaturated, aliphatic carboxylic acids, such as oleic acid), and alkylated malonic and succinic acids, such as octadecylsuccinic acid.

Suitable cycloaliphatic dicarboxylic acids are 1,3-cyclobutanedicarboxylic acid, 1,3-cyclopentanedicarboxylic acid, 1,3- and 1,4-cyclohexanedicarboxylic acid, 1,3- and 1,4-(dicarboxymethyl)cyclohexane and 4,4'-dicyclohexyldicarboxylic acid.

Suitable aromatic dicarboxylic acids are in particular terephthalic acid, isophthalic acid, o-phthalic acid, 1,3-, 1,4-, 2,6- and 2,7-naphthalenedicarboxylic acid, 4,4'-biphenyldicarboxylic acid, di(4-carboxyphenyl) sulfone, 4,4'-benzophenonedicarboxylic acid, 1,1,3-trimethyl-5-carboxy-3-(p-carboxyphenyl)indane, di(4-carboxyphenyl) ether, bis(p-carboxyphenyl)methane and bis(p-carboxyphenyl)ethane.

Preference is given to aromatic dicarboxylic acids, in particular terephthalic acid, isophthalic acid and 2,6-naphthalenedicarboxylic acid.

Further suitable dicarboxylic acids are those containing -CO-NH- groups; they are described in DE-A-2 414 349. Also suitable are dicarboxylic acids containing N-heterocyclic rings, for example those derived from carboxyalkylated, carboxyphenylated or carboxybenzylated monoamino-s-triazinedicarboxylic acids (cf. DE-A 2 121 184 and 2 533 675), mono- or bishydantoins, halogenated or unhalogenated benzimidazoles or parabanic acid. The carboxyalkyl groups in these compounds can contain from 3 to 20 carbon atoms.

Suitable aliphatic diols are linear and branched aliphatic glycols, in particular those having from 2 to 12, in particular from 2 to 6, carbon atoms in a molecule, for example ethylene glycol, 1,2- and 1,3-propylene glycol, 1,2-, 1,3-, 2,3- and 1,4-butanediol, pentyl glycol, neopentyl glycol, 1,6-hexanediol and 1,12-dodecanediol. An example of a suitable cycloaliphatic diol is 1,4-dihydroxycyclohexane. Further suitable aliphatic diols are, for example, 1,4-bis(hydroxymethyl)cyclohexane, aromatic-aliphatic diols, such as p-xylylene glycol and 2,5-dichloro-p-xylylene glycol, 2,2-(β -hydroxyethoxyphenyl)propane and polyoxyalkylene glycols, such as diethylene glycol, triethylene glycol, polyethylene glycol and polypropylene glycol. The alkylenediols are preferably linear and contain, in particular, from 2 to 4 carbon atoms.


Preferred diols are alkylenediols, 1,4-dihydroxycyclohexane and 1,4-bis(hydroxymethyl)cyclohexane. Particular preference is given to ethylene glycol, 1,4-butanediol and 1,2- and 1,3-propylene glycol.

Further suitable aliphatic diols are β -hydroxyalkylated, in particular β -hydroxyethylated bisphenols, such as 2,2-bis[4'-(β -hydroxyethoxy)phenyl]propane. Further bisphenols are given below.

A further group of suitable aliphatic diols comprises the heterocyclic diols described in DE-A 1 812 003, 2 342 432, 2 342 372 and 2 453 326. Examples are N,N'-bis(β -hydroxyethyl)-5,5-dimethylhydantoin, N,N'-bis(β -hydroxypropyl)-5,5-dimethylhydantoin, methylenebis[N-(β -hydroxyethyl)-5-methyl-5-ethylhydantoin], methylenebis[N-(β -hydroxyethyl)-5,5-dimethylhydantoin], N,N'-bis(β -hydroxyethyl)benzimidazolone, N,N'-bis(β -hydroxyethyl)tetrachlorobenzimidazolone and N,N'-bis(β -hydroxyethyl)tetrabromobenzimidazolone.

Suitable aromatic diols are monocyclic diphenols and in particular bicyclic diphenols

carrying a hydroxyl group on each aromatic ring. The term aromatic is preferably taken to mean hydrocarbon-aromatic radicals, for example phenylene or naphthylene. Besides, for example, hydroquinone, resorcinol and 1,5-, 2,6- and 2,7-dihydroxynaphthalene, particular mention should be made of the bisphenols which can be described by the following formulae:



The hydroxyl groups can be in the m-position, but in particular in the p-position, R' and R'' in these formulae can be alkyl having 1 to 6 carbon atoms, halogen, such as chlorine or

- 7 -

bromine, or in particular hydrogen, and A can be a direct bond or -O-, -S-, -(O)S(O)-, -C(O)-, -P(O)(C₁-C₂₀alkyl)-, substituted or unsubstituted alkylidene, cycloalkylidene or alkylene.

Examples of substituted or unsubstituted alkylidene are ethylidene, 1,1- and 2,2-propylidene, 2,2-butylidene, 1,1-isobutylidene, pentylidene, hexylidene, heptylidene, octylidene, dichloroethylidene and trichloroethylidene.

Examples of substituted or unsubstituted alkylene are methylene, ethylene, phenylmethylene, diphenylmethylene and methylphenylmethylene. Examples of cycloalkylidene are cyclopentylidene, cyclohexylidene, cycloheptylidene and cyclooctylidene.

Examples of bisphenols are bis(p-hydroxyphenyl) ether and thioether, bis(p-hydroxyphenyl) sulfone, bis(p-hydroxyphenyl)methane, bis(4-hydroxyphenyl)-2,2'-biphenyl, phenylhydroquinone, 1,2-bis(p-hydroxyphenyl)ethane, 1-phenylbis(p-hydroxyphenyl)methane, diphenylbis(p-hydroxyphenyl)methane, diphenylbis(p-hydroxyphenyl)ethane, bis(3,5-dimethyl-4-hydroxyphenyl) sulfone, bis(3,5-dimethyl-4-hydroxyphenyl)-p-diisopropylbenzene, bis(3,5-dimethyl-4-hydroxyphenyl)-m-diisopropylbenzene, 2,2-bis(3',5'-dimethyl-4'-hydroxyphenyl)propane, 1,1- and 2,2-bis(p-hydroxyphenyl)butane, 2,2-bis(p-hydroxyphenyl)hexafluoropropane, 1,1-dichloro- and 1,1,1-trichloro-2,2-bis(p-hydroxyphenyl)ethane, 1,1-bis(p-hydroxyphenyl)cyclopentane and in particular 2,2-bis(p-hydroxyphenyl)propane (bisphenol A) and 1,1-bis(p-hydroxyphenyl)cyclohexane (bisphenol C)

Suitable polyesters of hydroxycarboxylic acids are, for example, polycaprolactone, polypivalolactone and the polyesters of 4-hydroxycyclohexanecarboxylic acid and 4-hydroxybenzoic acid.

Also suitable are polymers containing predominantly ester bonds, but which can also contain other bonds, for example polyester amides and polyesterimides.

Polyesters with aromatic dicarboxylic acids have achieved the greatest importance, in particular the polyalkylene terephthalates. Preference is therefore given to novel moulding compositions in which the polyester is built up from at least 30 mol%, preferably at least 40 mol%, of aromatic dicarboxylic acids and at least 30 mol%, preferably at least 40 mol%, of alkylenediols, preferably having from 2 to 12 carbon atoms, based on the polyester.

In this case, the alkylene diol is in particular linear and contains from 2 to 6 carbon atoms, for example ethylene glycol, trimethylene glycol, tetramethylene glycol and hexamethylene glycol, and the aromatic dicarboxylic acid is in particular terephthalic acid and/or isophthalic acid.

The novel process is likewise of particular interest when the polycondensate is a polyester.

Particularly suitable polyesters are PET, PBT and corresponding copolymers, especial preference being given to PET and its copolymers. The process also achieves particular importance in the case of PET recyclates, which are obtained, for example, from bottle collections, for example collections by the drinks industry. These materials preferably comprise terephthalic acid, 2,6-naphthalenedicarboxylic acid and/or isophthalic acid in combination with ethylene glycol and/or 1,4-bis(hydroxymethyl)cyclohexane.

The term polycarbonate (PC) is taken to mean both fresh polycarbonate and recycled polycarbonate. PC is obtained, for example, from bisphenol A and phosgene or a phosgene analogue, such as trichloromethyl chloroformate, triphosgene or diphenyl carbonate, by condensation, in the latter case generally with addition of a suitable transesterification catalyst, for example a borohydride, an amine, such as 2-methylimidazole or a quaternary ammonium salt; besides bisphenol A, other bisphenol components can be used in addition, and monomers which are halogenated on the benzene ring can also be employed. Particularly suitable bisphenol components which may be mentioned are 2,2-bis(4'-hydroxyphenyl)propane (bisphenol A), 2,4'-dihydroxydiphenylmethane, bis(2-hydroxyphenyl)methane, bis(4-hydroxyphenyl)methane, bis(4-hydroxy-5-propylphenyl)methane, 1,1-bis(4'-hydroxyphenyl)ethane, bis(4-hydroxyphenyl)cyclohexylmethane, 2,2-bis(4'-hydroxyphenyl)-1-phenylpropane, 2,2-bis(3',5'-dimethyl-4'-hydroxyphenyl)propane, 2,2-bis(3',5'-dibromo-4'-hydroxyphenyl)propane, 2,2-bis(3',5'-dichloro-4'-hydroxyphenyl)propane, 1,1-bis(4'-hydroxyphenyl)cyclododecane, 1,1-bis(3',5'-dimethyl-4'-hydroxyphenyl)cyclododecane, 1,1-bis(4'-hydroxyphenyl)-3,3,5-trimethylcyclohexane, 1,1-bis(4'-hydroxyphenyl)-3,3,5-tetramethylcyclohexane, 1,1-bis(4'-hydroxyphenyl)-3,3,5-trimethylcyclopentane and the bisphenols mentioned above. The polycarbonates may furthermore be branched by small amounts of monomers having a functionality of more than two (examples as given above for the polyesters).


The novel process is also of particular interest when the polycondensate is a polycarbo-

nale.

The polycondensate copolymers or blends which can be used in the novel process are prepared in a conventional manner from the starting polymers. The polyester component is preferably PBT and the PC component is preferably a PC based on bisphenol A. The polyester:PC ratio is preferably from 95:5 to 5:95, a ratio in which one component makes up at least 75 % being particularly preferred.

The invention achieves particular importance in the case of recycled polycondensates, as obtained from production waste, valuable material collections or return obligations, for example in the automobile industry or in the electrical sector. Here, the recycled polycondensates are thermally and/or hydrolytically damaged in a variety of ways. In addition, these recyclates can also contain minor amounts of admixed plastics having different structures, for example polyolefins, polyurethanes, ABS or PVC. These recyclates can also contain usual impurities, for example residues of dyes, adhesives, contact media or paints, traces of metal, traces of water, traces of oils and greases or inorganic salts.

Sterically hindered hydroxyphenylalkylphosphonic esters and monoesters have been disclosed, for example, in US-A-4 778 840 and are, for example, compounds of the formula I



in which

R₁ is isopropyl, tert-butyl, cyclohexyl or cyclohexyl which is substituted by 1-3 C₁-C₄-alkyl groups,

R₂ is hydrogen, C₁-C₄alkyl, cyclohexyl or cyclohexyl which is substituted by 1-3 C₁-C₄-alkyl groups,

R₃ is C₁-C₂₀alkyl, or unsubstituted or C₁-C₄alkyl-substituted phenyl or naphthyl,

R₄ is hydrogen, C₁-C₂₀alkyl, unsubstituted or C₁-C₄alkyl-substituted phenyl or naphthyl;

or is $\frac{\text{M}^{r+}}{r}$,

M^{r+} is an r-valent metal cation,

- 10 -

n is 1, 2, 3, 4, 5 or 6, and

r is 1, 2 or 3.

C₁-C₂₀alkyl substituents are radicals such as methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, stearyl or corresponding branched isomers; C₂-C₄alkyl radicals are preferred.

C₁-C₄alkyl-substituted phenyl or naphthyl, which preferably contains 1 to 3, in particular 1 or 2, alkyl groups, is, for example, o-, m- or p-methylphenyl, 2,3-dimethylphenyl, 2,4-dimethylphenyl, 2,5-dimethylphenyl, 2,6-dimethylphenyl, 3,4-dimethylphenyl, 3,5-dimethylphenyl, 2-methyl-6-ethylphenyl, 4-tert-butylphenyl, 2-ethylphenyl, 2,6-diethylphenyl, 1-methylnaphthyl, 2-methylnaphthyl, 4-methylnaphthyl, 1,6-dimethylnaphthyl or 4-tert-butylnaphthyl.

C₁-C₄alkyl-substituted cyclohexyl, which preferably contains 1 to 3, in particular 1 or 2, branched or unbranched alkyl radicals, is, for example, cyclopentyl, methylcyclopentyl, dimethylcyclopentyl, cyclohexyl, methylcyclohexyl, dimethylcyclohexyl, trimethylcyclohexyl or tert-butylcyclohexyl.



A monovalent, divalent or trivalent metal cation is preferably an alkali metal cation, alkaline earth metal cation, heavy-metal cation or aluminium cation, for example Na⁺, K⁺, Mg⁺⁺, Ca⁺⁺, Ba⁺⁺, Zn⁺⁺ or Al⁺⁺⁺. Particular preference is given to Ca⁺⁺.

Preferred compounds of the formula I are those which contain at least one tert-butyl group as R₁ or R₂. Very particular preference is given to compounds in which R₁ and R₂ are simultaneously tert-butyl.

n is preferably 1 or 2, very particularly preferably 1.

Very particularly preferred sterically hindered hydroxyphenylalkylphosphonic esters and monoesters are the compounds of the formula II and III.

- 11 -




The compound of the formula II is commercially available as Irganox[®]1222 (Ciba-Geigy) and that of the formula III is commercially available as Irganox[®]1425 (Ciba-Geigy).

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of a sterically hindered hydroxyphenylalkylphosphonic ester or monoester are employed.

Polyfunctional, in particular difunctional, compounds from the epoxide class in the sense of this invention can have an aliphatic, aromatic, cycloaliphatic, araliphatic or heterocyclic structure; they contain epoxide groups as side groups or these groups form part of an alicyclic or heterocyclic ring system. The epoxide groups are preferably bonded to the remainder of the molecule as glycidyl groups via ether or ester bonds, or the compounds are N-glycidyl derivatives of heterocyclic amines, amides or imides. Epoxides of these types are known in general terms and are commercially available.

The epoxides contain, for example, two epoxide radicals, for example those of the formula IV



in which, when R₅ and R₇ are hydrogen, R₆ is hydrogen or methyl and p = 0; or, when R₅ and R₇ together are -CH₂-CH₂- or -CH₂-CH₂-CH₂-, R₆ is hydrogen and p = 0 or 1, where these radicals are bonded directly to carbon, oxygen, nitrogen or sulfur atoms.

Examples of epoxides which may be mentioned are:

1. Diglycidyl and di(β -methylglycidyl) esters obtainable by reacting a compound containing two carboxyl groups in the molecule and epichlorohydrin or glycerol dichlorohydrin or β -methylepichlorohydrin. The reaction is preferably carried out in the presence of bases.

The compounds containing two carboxyl groups in the molecule can be aliphatic dicarboxylic acids. Examples of these dicarboxylic acids are glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid or dimerized or trimerized linoleic acid.

However, it is also possible to employ cycloaliphatic dicarboxylic acids, for example tetrahydrophthalic acid, 4-methyltetrahydrophthalic acid, hexahydrophthalic acid or 4-methylhexahydrophthalic acid.

It is also possible to use aromatic dicarboxylic acids, for example phthalic acid or isophthalic acid.

2. Diglycidyl or di(β -methylglycidyl) ethers obtainable by reacting a compound containing two free alcoholic hydroxyl groups and/or phenolic hydroxyl groups and a suitably substituted epichlorohydrin under alkaline conditions or in the presence of an acid catalyst followed by alkali treatment.

Ethers of this type are derived, for example, from acyclic alcohols, such as ethylene glycol, diethylene glycol and higher poly(oxyethylene) glycols, propane-1,2-diol, or poly(oxypropylene) glycols, propane-1,3-diol, butane-1,4-diol, poly(oxytetramethylene) glycols, pentane-1,5-diol, hexane-1,6-diol, sorbitol and from polyepichlorohydrins.

However, they are also derived, for example, from cycloaliphatic alcohols, such as 1,3- or 1,4-dihydroxycyclohexane, bis(4-hydroxycyclohexyl)methane, 2,2-bis(4-hydroxycyclohexyl)propane or 1,1-bis(hydroxymethyl)cyclohex-3-ene, or they contain aromatic rings, such as N,N-bis(2-hydroxyethyl)aniline or p,p'-bis(2-hydroxyethylamino)diphenylmethane.

The epoxide compounds can also be derived from monocyclic phenols, for example from resorcinol, pyrocatechol or hydroquinone; or they are based on polycyclic phenols, for

example on 4,4'-dihydroxybiphenyl, bis(4-hydroxyphenyl)methane, 2,2-bis(4-hydroxyphenyl)propane, 2,2-bis(3,5-dibromo-4-hydroxyphenyl)propane, 4,4'-dihydroxydiphenyl sulfone, 9,9'-bis(4-hydroxyphenyl)fluorene, or on condensation products of phenols with formaldehyde obtained under acid conditions, such as phenol novolaks.

3. Di(N-glycidyl) compounds are obtainable, for example, by dehydrochlorinating the products of the reaction of epichlorohydrin with amines containing two amino hydrogen atoms. These amines are, for example, aniline, toluidine, n-butylamine, bis(4-amino-phenyl)methane, m-xylylenediamine or bis(4-methylaminophenyl)methane.

However, the di(N-glycidyl) compounds also include N,N'-diglycidyl derivatives of cycloalkyleneureas, such as ethyleneurea or 1,3-propyleneurea, and N,N'-diglycidyl derivatives of hydantoins, such as of 5,5-dimethylhydantoin.

4. Di(S-glycidyl) compounds, such as di-S-glycidyl derivatives derived from dithiols, for example ethane-1,2-dithiol or bis(4-mercaptomethylphenyl) ether.

5. Epoxides containing a radical of the formula IV in which R₅ and R₇ together are -CH₂-CH₂- and n is 0, for example bis(2,3-epoxycyclopentyl) ether, 2,3-epoxycyclopentyl glycidyl ether or 1,2-bis(2,3-epoxycyclopentoxo)ethane; epoxides containing a radical of the formula IV in which R₅ and R₇ together are -CH₂-CH₂- and n is 1, for example (3',4'-epoxy-6'-methylcyclohexyl)methyl 3,4-epoxy-6-methylcyclohexanecarboxylate.

The abovementioned difunctional epoxides can, for example owing to the production process, contain small amounts of monofunctional or trifunctional components.

Predominant use is made of diglycidyl compounds containing aromatic structures.

It may also be possible to employ a mixture of epoxides having different structures.

On the other hand, trifunctional and polyfunctional epoxides can be added in addition to give branches if desired. Such epoxides are, for example, a) liquid bisphenol A diglycidyl ethers, such as Araldit[®]GY 240, Araldit[®]GY 250, Araldit[®]GY 260, Araldit[®]GY 266, Araldit[®]GY 2600, Araldit[®]MY 790; b) solid bisphenol A diglycidyl ethers, such as Araldit[®]GT 6071, Araldit[®]GT 7071, Araldit[®]GT 7072, Araldit[®]GT 6063, Araldit[®]GT 7203, Araldit[®]GT 6064, Araldit[®]GT 7304, Araldit[®]GT 7004,

- 14 -

Araldit®GT 6084, Araldit®GT 1999, Araldit®GT 7077, Araldit®GT 6097, Araldit®GT 7097, Araldit®GT 7008, Araldit®GT 6099, Araldit®GT 6608, Araldit®GT 6609, Araldit®GT 6610; c) liquid bisphenol F diglycidyl ethers, such as Araldit®GY 281, Araldit®GY 282, Araldit®PY 302, Araldit®PY 306; d) solid polyglycidyl ethers of tetraphenylethane, such as CG Epoxy Resin®0163; e) solid and liquid polyglycidyl ethers of phenol-formaldehyde novolak, such as EPN 1138, EPN 1139, GY 1180, PY 307; f) solid and liquid polyglycidyl ethers of o-cresol-formaldehyde novolak, such as ECN 1235, ECN 1273, ECN 1280, ECN 1299; g) liquid glycidyl ethers of alcohols, such as Shell® glycidyl ether 162, Araldit®DY 0390, Araldit®DY 0391; h) liquid glycidyl esters of carboxylic acids, such as Shell®Cardura E terephthalates, trimellitates, Araldit®PY 284 or mixtures of aromatic glycidyl esters, for example Araldit®PT 910; i) solid heterocyclic epoxy resins (triglycidyl isocyanurate), such as Araldit®PT 810; j) liquid cycloaliphatic epoxy resins, such as Araldit®CY 179; k) liquid N,N,O-triglycidyl ethers of p-aminophenol, such as Araldit®MY 0510; l) tetraglycidyl-4-4'-methylenbenzamine or N,N,N',N'-tetraglycidyl diaminophenylmethane, such as Araldit®MY 720 and Araldit®MY 721.


The difunctional epoxides are particularly preferably diglycidyl ethers based on bisphenols, for example on 2,2-bis(4-hydroxyphenyl)propane (bisphenol A), bis(4-hydroxyphenyl) sulfone (bisphenol S) or mixtures of bis(ortho/para-hydroxyphenyl)methane (bisphenol F).

Very particular preference is given to solid epoxides of the bisphenol A diglycidyl ether type, for example Araldit®GT 6071, GT 7071, GT 7072, GT 6097 and GT 6099 or liquid epoxides of the bisphenol F type, such as Araldit®GY 281 or PY 306.

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of a diepoxide are employed.

Polyfunctional, in particular trifunctional, compounds from the oxazoline class in the sense of this invention are known and are described, for example, in EP-A-0 583 807 and are, for example, compounds of the formula V

- 15 -



in which R_8 , R_9 , R_{10} and R_{11} , independently of one another, are hydrogen, halogen, C_1 - C_{20} alkyl, C_4 - C_{15} cycloalkyl, unsubstituted or C_1 - C_4 alkyl-substituted phenyl, C_1 - C_{20} alkoxy or C_2 - C_{20} carboxyalkyl,

if $t = 3$,

R_{12} is a trivalent linear, branched or cyclic aliphatic radical having 1 to 18 carbon atoms, which may be interrupted by oxygen, sulfur or $\text{N}-R_{13}$, or R_{12} is furthermore an unsubstituted or C_1 - C_4 alkyl-substituted benzenetriyl radical,

if $t = 2$,

R_{12} is a divalent linear, branched or cyclic aliphatic radical having 1 to 18 carbon atoms, which may be interrupted by oxygen, sulfur or $\text{N}-R_{13}$, or R_{12} is furthermore an unsubstituted or C_1 - C_4 alkyl-substituted phenylene radical,

R_{13} is C_1 - C_8 alkyl, and

t is 2 or 3.

Halogen is, for example, fluorine, chlorine, bromine or iodine, particularly preferably chlorine.

C_1 - C_{20} alkyl is a branched or unbranched radical, for example methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, eicosyl or docosyl. A preferred meaning of R_8 , R_9 , R_{10} and R_{11} is C_1 - C_{12} alkyl, in particular C_1 - C_8 alkyl, for example C_1 - C_4 alkyl.

C₄-C₁₅cycloalkyl, in particular C₅-C₁₂cycloalkyl, is, for example, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl or cyclododecyl. Preference is given to C₅-C₈cycloalkyl, in particular cyclohexyl.

C₁-C₄alkyl-substituted phenyl which preferably contains 1 to 3, in particular 1 or 2, alkyl groups is, for example, o-, m- or p-methylphenyl, 2,3-dimethylphenyl, 2,4-dimethylphenyl, 2,5-dimethylphenyl, 2,6-dimethylphenyl, 3,4-dimethylphenyl, 3,5-dimethylphenyl, 2-methyl-6-ethylphenyl, 4-tert-butylphenyl, 2-ethylphenyl or 2,6-diethylphenyl.

C₁-C₂₀alkoxy is a branched or unbranched radical, for example methoxy, ethoxy, propoxy, isopropoxy, n-butoxy, isobutoxy, pentoxy, isopentoxy, hexyloxy, heptyloxy, octyloxy, decyloxy, tetradecyloxy, hexadecyloxy or octadecyloxy. A preferred meaning of R₈, R₉, R₁₀ and R₁₁ is C₁-C₁₂alkoxy, in particular C₁-C₈alkoxy, for example C₁-C₄alkoxy.

C₂-C₂₀Carboxyalkyl is a branched or unbranched radical, for example carboxymethyl, carboxyethyl, carboxypropyl, carboxybutyl, carboxypentyl, carboxyhexyl, carboxyheptyl, carboxyoctyl, carboxynonyl, carboxydecyl, carboxyundecyl, carboxydodecyl, 2-carboxy-1-propyl, 2-carboxy-1-butyl or 2-carboxy-1-pentyl. A preferred meaning of R₈, R₉, R₁₀ and R₁₁ is C₂-C₁₂carboxyalkyl, in particular C₂-C₈carboxyalkyl, for example C₂-C₄carboxyalkyl.

A trivalent linear, branched or cyclic aliphatic radical having 1 to 18 carbon atoms, which may be interrupted by oxygen, sulfur or $\text{N}-\text{R}_{13}$, means that the three bonds may be on the same or on different atoms. Examples thereof are methanetriyl, 1,1,1-ethanetriyl, 1,1,1-propanetriyl, 1,1,1-butanetriyl, 1,1,1-pentanetriyl, 1,1,1-hexanetriyl, 1,1,1-heptanetriyl, 1,1,1-octanetriyl, 1,1,1-nonanetriyl, 1,1,1-decanetriyl, 1,1,1-undecanetriyl, 1,1,1-dodecanetriyl, 1,2,3-propanetriyl, 1,2,3-butanetriyl, 1,2,3-pentanetriyl, 1,2,3-hexanetriyl, 1,1,3-cyclopentanetriyl, 1,3,5-cyclohexanetriyl, 3-oxo-1,1,5-pentanetriyl, 3-thio-1,1,5-pentanetriyl or 3-methylamino-1,1,5-pentanetriyl.

A divalent linear, branched or cyclic aliphatic radical having 1 to 18 carbon atoms, which may be interrupted by oxygen, sulfur or $\text{N}-\text{R}_{13}$, means that the two bonds may be on the same or on different atoms. Examples thereof are methylene, ethylene, propylene, butylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, undecylene or dode-

cylene.


Unsubstituted or C_1 - C_4 alkyl-substituted benzenetriyl, which preferably contains 1 to 3, in particular 1 or 2, alkyl groups, is, for example, 1,2,4-benzenetriyl, 1,3,5-benzenetriyl, 3-methyl-1,2,4-benzenetriyl or 2-methyl-1,3,5-benzenetriyl. Particular preference is given to 1,2,4-benzenetriyl and 1,3,5-benzenetriyl.

Of particular interest are compounds of the formula V in which

R_8 , R_9 , R_{10} and R_{11} , independently of one another, are hydrogen or C_1 - C_4 alkyl, and R_{12} is 1,2,4-benzenetriyl or 1,3,5-benzenetriyl.

Of especial interest are compounds of the formula V, for example 2,2',2''-(1,3,5-benzenetriyl)tris-2-oxazoline; 2,2',2''-(1,2,4-benzenetriyl)tris-4,4-dimethyl-2-oxazoline; 2,2',2''-(1,3,5-benzenetriyl)tris-4,4-dimethyl-2-oxazoline; 2,2',2''-(1,2,4-benzenetriyl)tris-5-methyl-2-oxazoline; or 2,2',2''-(1,3,5-benzenetriyl)tris-5-methyl-2-oxazoline.



Preferred difunctional compounds from the bisoxazoline class in the sense of this invention have been described by T. Loontjens et al., Makromol. Chem., Macromol. Symp. 75, 211-216 (1993) and are, for example, compounds of the formula



- 18 -

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of an oxazoline are employed. Further preferred bisoxazolines are described in F. Böhme et al., *Die Angewandte Makromolekulare Chemie* **224**, 167-178 (1995) and in DE-A-4 140 333.

Polyfunctional, in particular difunctional, compounds from the oxazine or oxazolone class in the sense of this invention are known and have been described, for example, by H. Inata et al., *J. Applied Polymer Science* Vol. **32**, 4581-4594 (1986) and are, for example, compounds of the formula VIa or VIb




in which

R_{14} is a direct bond or unsubstituted or C_1 - C_4 alkyl-substituted phenylene, and R_{15} and R_{16} , independently of one another, are hydrogen or C_1 - C_4 alkyl.

Special preference is given to compounds of the formula VIa and VIb in which R_{14} is a direct bond, in particular 2,2'-bis(4H-3,1-benzoxazin-4-one).

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of an oxazine or oxazolone are employed.

Polyfunctional, in particular difunctional, compounds from the isocyanate class in the sense of this invention are known and are, for example, compounds of the formula VII



in which R_{23} is C_1 - C_{20} alkylene or polymethylene, arylene, aralkylene or cycloalkylene.


Preferred diisocyanates are tetramethylene diisocyanate, hexamethylene diisocyanate, dodecamethylene diisocyanate, eicosane 1,20-diisocyanate, 4-butylhexamethylene diisocyanate, 2,2,4- and 2,4,4-trimethylhexamethylene diisocyanate, $OCN(CH_2)_2O(CH_2)_2NCO$, toluene 2,4-diisocyanate, p-phenylene diisocyanate, xylylene diisocyanates, 3-isocyanatomethyl-3,5,5-trimethylcyclohexyl isocyanate, naphthalene diisocyanates, sulfonyl diisocyanates, 3,3', 4,4'- and 3,4'-diisocyanates of diphenylmethane, 2,2-diphenylpropane and diphenyl ether, 3,3'-dimethyl-4,4'-diisocyanatobiphenyl, 3,3'-dimethoxy-4,4'-diisocyanatobiphenyl and 4,4'-diisocyanatodiphenylmethane.

These diisocyanates are commercially available or can be prepared from commercially available amines.

However, it is also possible to employ diisocyanate generators, such as polymeric urethanes, uretdione dimers and higher oligomers, cyanurate polymers, urethanes and polymeric urethanes of cyanurate polymers and thermally dissociable adducts of Schiff's bases.


Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of an isocyanate are employed.

Polyfunctional, in particular difunctional, compounds from the anhydride class in the sense of this invention are known and are, for example, compounds of the formula VIII




in which R_{24} is a radical of the formulae (VIIIa)-(VIIIj)


- 20 -




(VIIIa)




(VIIIb)




(VIIIc)




(VIIId)




(VIIIe)




(VIIIf)




(VIIIg)



(VIIIh)



(VIIIi)



(VIIIj)

in which R_{25} is $-CH_2-$, $-CH(CH_3)-$, $-C(CH_3)_2-$, $-C(CF_3)_2-$, $-S-$, $-O-$, $-(O)S(O)-$, $-NHCO-$, $-CO-$ or $-P(O)(C_1-C_{20}alkyl)-$ and in which the aromatic rings in the formulae VIIIa to VIIIe are unsubstituted or substituted by one or more C_1-C_6alkyl groups, $C_1-C_6alkoxy$ groups or halogen atoms.


An example of a trifunctional anhydride is mellitic anhydride.

Preference is given to tetracarboxylic dianhydrides containing aromatic rings. These tetracarboxylic anhydrides are commercially available.

It may also be possible to employ a mixture of tetracarboxylic dianhydrides having different structures.





Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of an anhydride are employed.

Polyfunctional, in particular difunctional, compounds from the acyllactam class in the sense of this invention are known and are, for example, compounds of the formula IX



in which s is a number from 1 to 16, in particular from 5 to 10, and


R_{26} is an aromatic radical, for example one of the formulae:



; where R_{27} is one of the radicals $-\text{CH}_2-$, $-\text{C}(\text{O})-$, $-\text{P}(\text{O})(\text{C}_1-\text{C}_{18}\text{alkyl})-$, $-(\text{O})\text{S}(\text{O})-$, $-\text{O}-$ or $-\text{S}-$.

Trifunctional compounds from the acyllactam class in the sense of this invention are known and are, for example, compounds of the formula IXa

- 22 -




in which z is a number from 1 to 16, in particular from 3 to 9.

Preference is given to trifunctional acyllactams of the formula IXa in which the lactam rings are caprolactam or laurolactam.

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of an acyllactam are employed.

Polyfunctional, in particular difunctional, compounds from the maleimide class in the sense of this invention are known and are, for example, compounds of the formula X




in which

R_{28} is an aliphatic, aromatic, cycloaliphatic or heterocyclic radical; and R_{29} and R_{30} , independently of one another, are hydrogen, C_1 - C_4 alkyl, C_1 - C_6 alkoxy, phenyl or phenoxy.

The aliphatic, aromatic, cycloaliphatic or heterocyclic radicals have a maximum of 40 carbon atoms, can be unsubstituted or substituted, and can also be interrupted by -O-, -S-, $-(CH_2)_{1-6}$ -, $-C(O)-$, $-P(O)(C_1-C_{18}alkyl)-$ or $-(O)S(O)-$ (which represents the radical

- 23 -




hydroxyl, phenyl and phenoxy.

An aliphatic radical R_{28} is, for example, a $C_1\text{-}C_{18}$ polymethylene radical, which can be derived from alkyl radicals, such as methyl, ethyl, n-propyl, n-butyl, sec-butyl, tert-butyl, n-hexyl, n-octyl, 2-ethylhexyl, n-nonyl, n-decyl, n-undecyl, n-dodecyl, n-tridecyl, n-tetradecyl, n-hexadecyl or n-octadecyl, or from further branched isomers.

An aromatic radical R_{28} is, for example, a radical having 6-40 carbon atoms, such as phenylene, biphenylene or naphthylene or represents phenylene or biphenylene radicals linked by one of the groups such as -O-, -S-, $-(CH_2)_{1-6}$ -, -C(O)-, $-P(O)(C_1\text{-}C_{18}\text{alkyl})$ - or $-(O)S(O)$ -.

A cycloaliphatic radical R_{28} is, for example, a radical having 5-10 carbon atoms, such as cyclopentylene, cyclohexylene or cyclooctylene.


A heterocyclic radical R_{28} is, for example, an N-containing 5- or 6-membered ring, such as pyridylene, pyridazylene or pyrazolyne.



-C(O)-, -P(O)(C₁-C₁₈alkyl)-, -(O)S(O)-, -O- or -S-.

R₂₉ and R₃₀, independently of one another, are preferably hydrogen or C₁-C₄alkyl; R₂₉ is particularly preferably hydrogen and R₃₀ is particularly preferably hydrogen or methyl; and R₂₉ and R₃₀ are very particularly preferably hydrogen.

Very particular preference is given to compounds of the formula



Bismaleimides are obtained by reacting diamines with maleic anhydride, and some are commercially available. Further suitable bismaleimides are described in WO-A-93/24 488 (T.C. Morton et al.).

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of a maleimide are employed.


Polyfunctional compounds from the alcohol class in the sense of this invention are known and are, for example, pentaerythritol, dipentaerythritol, tripentaerythritol, bistrimethylol-

- 25 -

propane, bistrimethylolethane, trismethylolpropane, sorbitol, maltitol, isomaltitol, lactitol, lycasine, mannitol, lactose, leucrose, tris(hydroxyethyl) isocyanurate, palatinitol, tetramethylolcyclohexanol, tetramethylolcyclopentanol, tetramethylolcyclopyranol, glycerol, diglycerol, polyglycerol or 1-0- α -D-glycopyranosyl-D-mannitol dihydrate. Particular preference is given to pentaerythritol, dipentaerythritol and tris(hydroxyethyl) isocyanurate.

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of a polyfunctional alcohol are employed.

Polyfunctional, in particular difunctional, compounds from the carbodiimide class in the sense of this invention are known and are, for example, compounds of the formula XI



in which

R_{40} , R_{41} and R_{42} , independently of one another, are C_1 - C_{12} alkylene, C_6 - C_{13} cycloalkylene or unsubstituted or C_1 - C_4 alkyl-substituted phenylene or naphthylene,

X_1 and X_2 , independently of one another, are hydrogen, $-NH-CO-N \begin{smallmatrix} R_{43} \\ R_{44} \end{smallmatrix}$ or $-NH-CO-OR_{45}$.

where

R_{43} , R_{44} and R_{45} , independently of one another, are C_1 - C_{12} alkyl, C_6 - C_{13} cycloalkyl or unsubstituted or C_1 - C_4 alkyl-substituted phenyl or naphthyl, and

v is a number from 0 to 100.

C_1 - C_{12} Alkylene is a branched or unbranched radical, for example methylene, ethylene, propylene, tetramethylene, pentamethylene, hexamethylene, heptamethylene, octamethylene, decamethylene or dodecamethylene. A preferred meaning of R_{43} , R_{44} and R_{45} is, for example, C_2 - C_{10} alkylene, in particular C_2 - C_8 alkylene.

C_6 - C_{13} Cycloalkylene is a saturated hydrocarbon group having two free valences and containing at least one ring unit and is, for example, cyclohexylene, cycloheptylene or cyclo-octylene. Preference is given to cyclohexylene.


Unsubstituted or C_1 - C_4 alkyl-substituted phenylene or naphthylene is, for example, 1,2-, 1,3- or 1,4-phenylene or 1,2-, 1,3-, 1,4-, 1,6-, 1,7-, 2,6- or 2,7-naphthylene. 1,4-Phenylene is preferred.

C_1 - C_{12} Alkyl is a branched or unbranched radical, for example methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl or 1,1,3,3-tetramethylpentyl.

C_6 - C_{13} Cycloalkyl is, for example, cyclohexyl, cycloheptyl, cyclooctyl or cyclododecyl. Preference is given to C_6 - C_8 cycloalkyl, in particular cyclohexyl.


C_1 - C_4 Alkyl-substituted phenyl or naphthyl, which preferably contains 1 to 3, in particular 1 or 2, alkyl groups, is, for example, o-, m- or p-methylphenyl, 2,3-dimethylphenyl, 2,4-dimethylphenyl, 2,5-dimethylphenyl, 2,6-dimethylphenyl, 3,4-dimethylphenyl, 3,5-dimethylphenyl, 2-methyl-6-ethylphenyl, 4-tert-butylphenyl, 2-ethylphenyl, 2,4,6-triisopropylphenyl, 2,6-diethylphenyl, 2-methylnaphthyl or 1-methylnaphthyl.

An especially preferred carbodiimide is poly(2,4,6-triisopropyl-1,3-phenylenecarbodiimide) of the formula XIa



A further especially preferred carbodiimide is commercially available as stabilizer 7000® (manufacturer: Raschig, Germany) of the formula XIb


- 27 -



Further suitable carbodiimides are described in EP-A-0 623 589 and in EP-A-0 628 541.

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of a polyfunctional carbodiimide are employed.

Polyfunctional compounds from the ester class in the sense of this invention are known and are described, for example, in EP-A-0 565 487. Preferred polyfunctional esters are, for example, compounds of the formula XII




in which

R_{50} is C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl, phenyl or C_7 - C_9 phenylalkyl,

R_{51} is hydrogen, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl, phenyl or C_7 - C_9 phenylalkyl,

q is 0, 1 or 2,



above,

m is an integer in the range from 0 to 3,


R_{53} is C_1 - C_8 alkyl, and

- 28 -

w is an integer in the range from 2 to 6, where,


if $n = 2$,

R_{52} is a divalent radical of a hexose, a divalent radical of a hexitol, $\begin{array}{c} -CH_2 \\ | \\ -CH_2-C-CH_2OH \\ | \\ CH_2OH \end{array}$,





if $n = 3$,

R_{52} is a trivalent radical of a hexose, a trivalent radical of a hexitol, $\begin{array}{c} CH_2CH_2- \\ | \\ -CH_2CH_2-N-CH_2CH_2- \end{array}$



if $n = 4$,

R_{52} is a tetravalent radical of a hexose, a tetravalent radical of a hexitol,




if $n = 5$,

R_{52} is a pentavalent radical of a hexose or a pentavalent radical of a hexitol, or

- 29 -

if $n = 6$,




C_1 - C_{18} alkyl is a branched or unbranched radical, for example methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl or octadecyl. One of the preferred meanings of R_{50} and R_{51} is C_1 - C_8 alkyl, in particular C_1 - C_4 alkyl, for example tert-butyl.

C_5 - C_{12} cycloalkyl is, for example, cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, cyclodecyl or cyclododecyl. One of the preferred meanings of R_{50} and R_{51} is C_5 - C_7 cycloalkyl. Particular preference is given to cyclohexyl.


C_7 - C_9 phenylalkyl is, for example, benzyl, α -methylbenzyl, α,α -dimethylbenzyl or 2-phenylethyl. Benzyl is preferred.

If, for $w = 2$ to 6, R_{52} is a w -valent radical of a hexose, this is derived, for example, from allose, altrose, glucose, mannose, gulose, idose, galactose or talose, i.e. in order to obtain the corresponding compounds of the formula XII, one, two, three, four, five or six -OH groups must be replaced by the ester group E-1,




in which R_{50} , R_{51} , q and Q are as defined above. For example, R_{52} can, for $w = 5$, be a

- 30 -






If R_{52} is the w -valent radical of a hexitol, the corresponding compounds of the formula XII are obtained by replacing w -OH groups by the abovementioned ester group E-1. R_{52} can,




group is derived from D-sorbitol.

Preferred compounds of the formula XII are also, for example,



- 31 -



A particularly preferred compound of the formula XII is pentaerythrityl tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate] [Irganox[®] 1010 (Ciba-Geigy AG)].

Based on 100 parts of polycondensate, preferably from 0.01 to 5 parts, particularly preferably from 0.02 to 2 parts, in particular from 0.05 to 1 part, of a polyfunctional ester are employed.

It may also be possible to employ a mixture of various polyfunctional compounds.

In addition to the sterically hindered hydroxyphenylalkylphosphonic ester or monoester and the polyfunctional compound, further stabilizers can be added to the polycondensate. These further stabilizers are known in general terms to the person skilled in the art and are selected with respect to the specific requirements of the final product. In particular, light stabilizers or antioxidants or further antioxidants can be added ("Plastics Additives Handbook", Ed. R. Gächter and H. Müller, Hanser Verlag, 3rd Edn., 1990; in particular pp. 88/89, 92/94, 251/252 and 258/259). It is likewise possible to add further additives, for example lubricants, mould-release agents, fillers or reinforcing materials, for example glass fibres, flameproofing agents, antistatics and, in particular in the case of PBT/PC recyclates, additives which prevent transesterification during processing.

The following may be mentioned as being particularly suitable:

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol,


- 32 -

2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example, 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.


1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-dodecylthiomethyl-4-nonylphenol.

1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-di-phenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis-(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4. Chroman derivatives of the formula



$-(CH_2)_3-CH(CH_3)-(CH_2)_3-CH(CH_3)-(CH_2)_3-CH(CH_3)_2$ or $-CH_2-CH_2-O-C(O)-Z$, and Z is



hydrogen, methyl or tert-butyl, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis-(3,6-di-sec-amylphenol), 4,4'-bis-(2,6-dimethyl-4-hydroxyphenyl) disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis-(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra-(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxydibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioterephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

1.8. Hydroxybenzylated malonates, for example dioctadecyl-2,2-bis-(3,5-di-tert-butyl-2-hydroxybenzyl)-malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)-malonate, di-dodecylmercaptoethyl-2,2-bis-(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine Compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris-

(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.

1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.14. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.15. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis-(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine.

1.18. Ascorbic acid (vitamin C)

1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfonyl)diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxydiphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylamino-phenol, 4-nonanoylamino-phenol, 4-dodecanoylamino-phenol, 4-octadecanoylamino-phenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, Bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- und dialkylated tert-butyldiphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- und dialky-

lated tert-butyl/tert-octylphenothiazines, a mixture of mono- und dialkylated tert-octylphenothiazines, N-allylphenothiazin, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-tetramethyl-piperid-4-yl)-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)-benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chloro-benzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis-(α,α -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, mixture of 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)-carbonylethyl]-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonylethyl]-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, and 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonylethyl)phenyl)benzotriazole, 2,2'-methylene-bis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-ylphenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol 300; $[R-CH_2CH_2-COO(CH_2)_3]_n$, where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, as for example 4-tertbutylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl) resorcinol, benzoyl resorcinol, 2,4-di-tertbutylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxy-

benzoate.

2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl α -cyano- β -methyl-p-methoxycinnamate, butyl α -cyano- β -methyl-p-methoxycinnamate, methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thio-bis-[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenyl undecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, the condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octyl-amino-2,6-dichloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitriлотriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butane-tetracarboxylate, 1,1'-(1,2-ethanediy)bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyloxy-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decan-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, the condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis-(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidin-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione, a mixture of 4-hexadecyloxy- and 4-stearyloxy-2,2,6,6-tetramethylpiperidine, a condensation product of N,N'-bis-

(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, a condensation product of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]); N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimid, N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimid, 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4,5]decane, a reaction product of 7,7,9,9-tetramethyl-2-cyclo-undecyl-1-oxa-3,8-diaza-4-oxospiro [4,5]decane und epichlorohydrin.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide and mixtures of ortho- and para-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxy-propyloxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxy-phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxy-propoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine.


3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl) hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenyl-propionyl) hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyl dihydrazide, oxanilide, isophthaloyl dihydrazide, sebacoil bisphenylhydrazide, N,N'-diacetyladiopoyl dihydrazide, N,N'-bis(salicyloyl)oxalyl dihydrazide, N,N'-bis(salicyloyl)-

thiopropionyl dihydrazide.






4. Phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite, diisodecyl-oxy-pentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosponite, 6-isooctyl-oxy-2,4,8,10-tetra-tert-butyl-12H-dibenz[d,g]-1,3,2-dioxaphosphocin, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methylphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethylphosphite.

Particular preference is given to the following phosphites:

tris-(2,4-di-tert-butylphenyl) phosphite;



- 40 -



Very particular preference is given to tris(2,4-di-tert-butylphenyl) phosphite.

5. Hydroxylamines, for example, N,N-dibenzylhydroxylamine, N,N-diethylhydroxyl-

amine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

6. Nitrones, for example, N-benzyl-alpha-phenyl-nitron, N-ethyl-alpha-methyl-nitron, N-octyl-alpha-heptyl-nitron, N-lauryl-alpha-undecyl-nitron, N-tetradecyl-alpha-tridecyl-nitron, N-hexadecyl-alpha-pentadecyl-nitron, N-octadecyl-alpha-heptadecyl-nitron, N-hexadecyl-alpha-heptadecyl-nitron, N-octadecyl-alpha-pentadecyl-nitron, N-heptadecyl-alpha-heptadecyl-nitron, N-octadecyl-alpha-hexadecyl-nitron, nitron derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

7. Thiosynergists, for example, dilauryl thiodipropionate or distearyl thiodipropionate.

8. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis(β -dodecylmercapto)propionate.

9. Polyamide stabilisers, for example, copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

10. Basic co-stabilisers, for example, melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or tin pyrocatecholate.

11. Nucleating agents, for example, inorganic substances such as talcum, metal oxides such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds such as ionic copolymers ("ionomers").

12. Fillers and reinforcing agents, for example, calcium carbonate, silicates, glass fibres,

glass bulbs, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite, wood flour and flours or fibers of other natural products, synthetic fibers.

13. Other additives, for example, plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

14. Benzofuranones and indolinones, for example those disclosed in US-A-4 325 863, US-A-4 338 244, US-A-5 175 312, US-A-5 216 052, US-A-5 252 643, DE-A-4 316 611, DE-A-4 316 622, DE-A-4 316 876, EP-A-0 589 839 or EP-A-0 591 102 or 3-[4-(2-acetoxyethoxy)phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butyl-benzofuran-2-one.

Preference is given here to light stabilizers from classes 2.1, 2.6 and 2.7, for example light stabilizers of the Chimassorb 944, Chimassorb 119, Tinuvin 234, Tinuvin 312, Tinuvin 622 and Tinuvin 770 type. Preference is furthermore given to aromatic phosphites and phosphonites.

The solid-phase postcondensation is carried out in a known manner. Reference is made in this respect to EP-A-0 090 915 or the article by S.A. Jabarin et al., Journal of Applied Polymer Science, Vol. 32, 5315-5335 (1986). In the novel process, the polycondensate is heated to a temperature from about 100 to 5°C below the melting point. In the particularly preferred novel process, the polycondensate is heated to a temperature of from about 60 to 5°C, in particular from 40 to 5°C, below the melting point. In this temperature range, the polycondensate is treated in a stream of inert gas or under vacuum until the desired high viscosity or, if desired, branching, crosslinking or partial crosslinking of the polycondensate has been achieved.

The sterically hindered hydroxyphenylalkylphosphonic ester or monoester and the polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters can, independently of one another, be, for the addition, in the form of li-

quids, powders, granules or in compacted form or alternatively on a support material, such as silica gel or together with a polymer powder or wax, such as a polyethylene wax.

From 0.01 to 5 parts of a sterically hindered hydroxyphenylalkylphosphonic ester or monoester or from 0.01 to 5 parts of a sterically hindered hydroxyphenylalkylphosphonic ester or monoester and from 0.01 to 5 parts of a polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters are preferably added per 100 parts of polycondensate. From 0.02 to 2 parts, in particular from 0.05 to 1 part, of a sterically hindered hydroxyphenylalkylphosphonic ester or monoester or from 0.02 to 2 parts, in particular from 0.05 to 1 part, of a sterically hindered hydroxyphenylalkylphosphonic ester or monoester and from 0.02 to 2 parts, in particular from 0.05 to 1 part, of a polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters are particularly preferably employed.

The amount of sterically hindered hydroxyphenylalkylphosphonic ester or monoester and polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters depends on the initial molecular weight of the polymer and on the final molecular weight desired. For example, for a severely damaged polycondensate, i.e. of low molecular weight, preference is given to a sterically hindered hydroxyphenylalkylphosphonic ester or monoester or a sterically hindered hydroxyphenylalkylphosphonic ester or monoester and the polyfunctional compound selected from the class consisting of epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters in the upper weight range. If, by contrast, only a slight increase in molecular weight is desired, the additive or additives is/are employed in low concentrations.

If a crosslinked or partially crosslinked, i.e. insoluble, polycondensate is desired, a relatively high concentration of the polyfunctional compound containing more than two reactive groups in the molecule is preferably employed.

It is furthermore possible to control the final molecular weight and the degree of crosslinking via the reaction time and via the temperature.

If the polycondensate is a recyclate, it can also be mixed with fresh material or employed together with fresh material, for example in a coextrusion process. Stabilization and molecular weight increase can in this case be carried out independently of one another.

The invention furthermore relates to the use of a sterically hindered hydroxyphenylalkylphosphonic ester or monoester for increasing the molecular weight of a polycondensate. The preferences regarding the use correspond to those for the process.

The invention furthermore relates to the use of a mixture comprising at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester and a polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters for increasing the molecular weight of a polycondensate. The preferences regarding the use correspond to those for the process.

The invention furthermore relates to a composition comprising a) a polycondensate recyclate, and b) at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester. The invention furthermore relates to a composition comprising a) a polycondensate recyclate, b) at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester and c) at least one polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters.

The preferences regarding the compositions correspond to those for the process.

The invention furthermore relates to polycondensates obtainable by the novel process.

The examples below illustrate the invention in greater detail without representing a limitation. Parts and percentages, as in the remainder of the description, relate to the weight, unless otherwise stated.

Examples 1 - 6: Molecular weight increase of used PET material by solid-phase condensation.

A used PET material from a bottle collection (origin: Switzerland) is extruded in a twin-screw extruder (Werner + Pfleiderer ZSK 25) at 260°C with the additives indicated in

Table 1, the extrudate is granulated, and the granules are subsequently subjected to solid-phase condensation in a tumble dryer at 230°C for 23 hours under a vacuum of approx. 1 mbar. The intrinsic viscosity $[\eta]$ of the polymer is determined using a solution of 1 g of the polymer in 100 g of a 1:1 mixture of o-dichlorobenzene and phenol at 30°C. The results are shown in Table 1. The higher the intrinsic viscosity, the greater the increase in molecular weight. The note "insoluble" in the "intrinsic viscosity" column means that the intrinsic viscosity could not be measured since 1 g of the polymer was not soluble in 100 g of a 1:1 mixture of o-dichlorobenzene and phenol at 30°C.


Table 1:

Example	Additives	Intrinsic viscosity $[\eta]$ in [dl/g]	
		after extrusion	after solid-phase condensation
1	—	0.44	0.89
2	0.25 % of Irganox 1425	0.47	1.08
3	0.25 % of Irganox 1222	0.51	1.18
4	0.25 % of Irganox 1425 0.25 % of Irganox 1010	0.47	1.18
5	0.25 % of Irganox 1425 0.25 % of pentaerythritol	0.48	insoluble
6	0.25 % of Irganox 1425 0.25 % of Araldit GT 6071	0.46	insoluble


Table 1 shows a clear increase in the intrinsic viscosity for Examples 2 to 6 according to the invention, indicating an increase in the molecular weight.

Irganox®1222 (Ciba-Geigy) is a compound of the formula II.

- 46 -



Irganox[®]1425 is a compound of the formula III.



Irganox[®]1010 (Ciba-Geigy) is pentaerythrityl tetrakis-[3-(3,5-di-tert-butyl-4-hydroxy-phenyl)propionate].

Araldit[®]GT 6071 (Ciba-Geigy) is bisphenol A diglycidyl ether having an epoxide number of 2.15-2.22 eq/kg and a softening range of 70-75°C.

Examples 7 and 8: Molecular weight increase of used PET material by solid-phase condensation.

A used PET material from a bottle collection (origin: Switzerland) is extruded in a twin-screw extruder (Werner + Pfleiderer ZSK 45) at 280°C with the additives indicated in Table 2, the extrudate is granulated, and the granules are subsequently subjected to solid-phase condensation in a tumble dryer at 230°C for 23 hours under a vacuum of approx. 1 mbar. The intrinsic viscosity $[\eta]$ of the polymer is determined analogously to Examples 1 to 6 using a solution of 1 g of the polymer in 100 g of a 1:1 mixture of o-dichlorobenzene and phenol at 30°C. The results are shown in Table 2. The higher the intrinsic viscosity, the greater the increase in molecular weight. The note "crosslinked" in the "intrinsic viscosity" column means that the intrinsic viscosity could not be measured since 1 g of the polymer was not soluble in 100 g of a 1:1 mixture of o-dichlorobenzene and phenol at 30°C.


- 47 -

Table 2:

Example	Additives	Intrinsic viscosity $[\eta]$ in [dl/g]					
		after extrusion	after solid-phase condensation at 230°C				
			1 hour	3 hours	5 hours	10 hours	23 hours
7	—	0.70	0.71	0.76	0.81	0.91	1.10
8	0.20 % of Irganox 1425 0.50 % of Araldit GT 6071	0.66	0.73	0.83	crosslinked	crosslinked	crosslinked

WHAT IS CLAIMED IS:

1. A process for increasing the molecular weight of polycondensates, which comprises heating a polycondensate in the temperature range below the melting point and above the glass transition temperature in the solid phase of the polymer with addition of at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester.
2. A process according to claim 1, wherein at least one polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters is additionally employed.
3. A process according to claim 1, wherein the polycondensate is a recycled polycondensate.
4. A process according to claim 1, wherein the sterically hindered hydroxyphenylalkylphosphonic ester or monoester is a compound of the formula I



in which

R₁ is isopropyl, tert-butyl, cyclohexyl or cyclohexyl which is substituted by 1-3

C₁-C₄alkyl groups,

R₂ is hydrogen, C₁-C₄alkyl, cyclohexyl or cyclohexyl which is substituted by 1-3 C₁-C₄-alkyl groups,

R₃ is C₁-C₂₀alkyl, or unsubstituted or C₁-C₄alkyl-substituted phenyl or naphthyl,

R₄ is hydrogen, C₁-C₂₀alkyl, unsubstituted or C₁-C₄alkyl-substituted phenyl or naphthyl;


or is $\frac{\text{M}^{r+}}{r}$,

M^{r+} is an r-valent metal cation,


n is 1, 2, 3, 4, 5 or 6, and

r is 1, 2 or 3.

5. A process according to claim 1, wherein the sterically hindered hydroxyphenylalkyl-phosphonic ester or monoester is a compound of the formula II or III




(II)



(III)

6. A process according to claim 1, wherein the polycondensate is a polyamide, a polyester, a polycarbonate or a copolymer of these polymers.
7. A process according to claim 1, wherein the polycondensate is a polyamide, preferably PA 6 or PA 6.6, or a corresponding recyclate or copolymer thereof.
8. A process according to claim 1, wherein the polycondensate is a polycarbonate.
9. A process according to claim 1, wherein the polycondensate is a PET.
10. A process according to claim 2, wherein the polyfunctional compound from the epoxide class is a compound containing epoxide radicals of the formula IV



in which, when R_5 and R_7 are hydrogen, R_6 is hydrogen or methyl and $p = 0$; or, when R_5 and R_7 together are $-\text{CH}_2-\text{CH}_2-$ or $-\text{CH}_2-\text{CH}_2-\text{CH}_2-$, R_6 is hydrogen and $p = 0$ or 1 , where these radicals are bonded directly to carbon, oxygen, nitrogen or sulfur atoms.

11. A process according to claim 2, wherein the polyfunctional compound from the alco-

hol class is pentaerythritol or dipentaerythritol.

12. A process according to claim 2, wherein the polyfunctional compound from the ester class is pentaerythrityl tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate].
13. A process according to claim 1, wherein from 0.01 to 5 parts of the sterically hindered hydroxyphenylalkylphosphonic ester or monoester are employed per 100 parts of polycondensate.
14. A process according to claim 2, wherein from 0.01 to 5 parts of the polyfunctional compound are employed per 100 parts of polycondensate.
15. A process according to claim 1, wherein the polycondensate is heated at from 100 to 5°C below the melting point in the solid phase.
16. The use of a sterically hindered hydroxyphenylalkylphosphonic ester or monoester for increasing the molecular weight of a polycondensate.
17. The use of a mixture comprising at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester and at least one polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters for increasing the molecular weight of a polycondensate.
18. A composition comprising
 - a) a polycondensate recycle, and
 - b) at least one sterically hindered hydroxyphenylalkylphosphonic ester or monoester according to claim 1.
19. A composition according to claim 18, which additionally comprises at least one polyfunctional compound selected from the class consisting of the epoxides, oxazolines, oxazolones, oxazines, isocyanates, anhydrides, acyllactams, maleimides, alcohols, carbodiimides and esters.
20. A polycondensate obtainable by a process according to claim 1 or 2.

INTERNATIONAL SEARCH REPORT

Intern. Application No.

PCT/EP 95/03937

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08K5/5333 C08L67/02 C08J11/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,A	WO,A,94 24188 (CIBA-GEIGY) 27 October 1994	1-6,9, 10,13, 16,18-20
X	see page 6, paragraph 4 see page 9, paragraph 5 see page 10, paragraph 5 see claims 1,2,6,7,10-16; examples ---	1,2
P,A	WO,A,95 23176 (CIBA-GEIGY) 31 August 1995	1-6,10, 16,18-20
X	see claims 1-10,13,14; examples 1,18 ---	1,2
X	EP,A,0 604 367 (CIBA-GEIGY) 29 June 1994 see page 4, line 2 - page 5, line 1; claims 1-14; examples ---	1-7,10, 16,18-20
	--- -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"A" document member of the same patent family

Date of the actual completion of the international search

24 January 1996

Date of mailing of the international search report

12.02.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Engel, S

INTERNATIONAL SEARCH REPORT

Intern al Application No

PCT/EP 95/03937

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	EP,A,0 628 588 (CIBA-GEIGY) 14 December 1994 see page 5, line 34 - line 36; claims 1,6-12; examples ---	1-7,10, 16,18-20
A	EP,A,0 559 953 (DAICEL CHEM. IND.) 15 September 1993 see claims 1,19,20,49; examples A3,A4 ---	1-6,8, 17,20
A	DATABASE WPI Section Ch, Week 9201 Derwent Publications Ltd., London, GB; Class A23, AN 92-002689 & JP,A,03 255 125 (DAICEL CHEM IND KK) , 14 November 1991 see abstract & CHEMICAL ABSTRACTS, vol. 116, no. 10, 9 March 1992 Columbus, Ohio, US; abstract no. 84447, 'Manufacture of polycarbonates of high molecular weight' see abstract ---	1-6,8
A	CHEMICAL ABSTRACTS, vol. 103, no. 20, 18 November 1985 Columbus, Ohio, US; abstract no. 161722, G. DZIN ET AL. 'Manufacrure of poly (ethylene terephthalate) with a reduced oligomer content II' see abstract & POLIMERI, vol. 6, no. 4-5, ZAGREB, pages 97-99, ---	1-6,9
A	EP,A,0 501 545 (AGFA-GEVAERT) 2 September 1992 see claims 1,4,5; examples 1,10 -----	1,9

INTERNATIONAL SEARCH REPORT

Internat. Application No

PCT/EP 95/03937

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WD-A-9424188	27-10-94	AU-B- 6677294	08-11-94
WD-A-9523176	31-08-95	AU-B- 1665895	11-09-95
EP-A-604367	29-06-94	CA-A- 2111905	23-06-94
		JP-A- 6239879	30-08-94
EP-A-628588	14-12-94	JP-A- 7010990	13-01-95
EP-A-559953	15-09-93	JP-A- 5310906	22-11-93
		US-A- 5391690	21-02-95
		US-A- 5387628	07-02-95
		US-A- 5278279	11-01-94
EP-A-501545	02-09-92	JP-A- 5155994	22-06-93
		US-A- 5185426	09-02-93